



Timberex Heavy Duty UV

Hard Wearing Oil for Commercial Use



New and Improved!



The new and improved Timberex Heavy Duty formulation now includes a UV-blocker which will inhibit the bleaching of the surface by harmful UV rays. Using natural, fast drying oils and resins which penetrate deeply into the wood. Filling and enriching the pores it cures to seal and protect from within. Specially formulated for high traffic areas, Timberex Heavy Duty UV has been used extensively in airports, sports halls, museums, art galleries, conference centres, offices etc.

- Cured and buffed surface has a highly wear and water-resistant finish with a deep satin sheen
- Colour is enriched and grain patterns are highlighted on the smooth, easily maintained surface

The Finest Natural Protection



Timberex Heavy Duty UV

Hard Wearing Oil for Commercial Use

AVAILABILITY

Available in 1 & 5 litre tins.

COVERAGE

8-12 m² per litre.

Coverage on end-grain wood will be greatly reduced. It is recommended that on 'end grain' wood, beech, cherry and other extremely porous woods, a extra coat of oils is applied to reduce excessive absorption.

EQUIPMENT

Drum sander, sandpaper including 120 grade for final preparatory sanding, buffing machine (150-300 rpm), wide brush or platform pad, Red grade (3M) nylon buffing pads, absorbent cloths and water bucket.

PREPARATION

Punch down any nail heads, fill any small holes or imperfections with proprietary coloured timber filler (plastic wood) and leave to cure. The wood should not have excessive gaps through which the product could seep and affect the bond of any adhesive layer or rooms below. Floors should be free from any barrier to penetration. Sand at least twice starting with coarse sandpaper, and use 120 grade maximum sandpaper for the final preparatory sanding. Clean the surface by vacuuming and damp wipe the entire floor using a very well wrung-out cloth, and allow to dry.

APPLICATION

It is advisable to test a small area first to ensure that the desired result is achieved. Timberex Heavy Duty UV is designed to deeply penetrate and protect from within the wood and must not be used to form a surface coating.

1. Apply the first coat of Timberex Heavy Duty UV using a wide brush, roller or platform pad. Accidental splashes on surrounding surfaces must be removed immediately. Keep moving the oil to areas where it is being absorbed. It

must not dry between coats.

2. Apply a second coat after 20-30 minutes or sooner, if the first coat is quickly absorbed.

3. Apply a third coat after 20-30 minutes.

Apply further coats until the wood will not absorb any more oil.

4. After a final 30 minutes, while there is a thin, even surface residue of unabsorbed Timberex Heavy Duty UV, it is important to thoroughly buff the wet surface with a red grade nylon pad at approximately 150 rpm.

5. Remove ALL unabsorbed Timberex Heavy Duty UV immediately with cloths, leaving a matt finish at this stage. Place all oil-impregnated cloths etc into a bucket filled with water. See 'SAFETY'.

6. Place all oil-impregnated cloths etc into a bucket filled with water. See 'SAFETY'.

7. When the surface has dried after 6-10 hours, it is important to thoroughly buff with a Red grade nylon pad to close the surface, provide a satin sheen and to remove any minor 'bleed-back'.

CLEANING OF APPLICATORS

Mild solvent, kerosene etc may be used.

CURING

The surface will normally be sufficiently dry to walk on after 24 hours. Dry vacuum only during the first 10 days and remove liquid spillages immediately. The surface will gradually increase in water-resistance. Any initial light water marking is easily removed by soft nylon pad in conjunction with Timberex Heavy Duty UV or one of the maintenance products from the Timberex Satin Oil Range.

MAINTENANCE

Floors which have been oiled for the first time should be treated with a Timberex Satin Oil product after 6-12 months and thereafter at annual intervals or as required. Timberex Bio-C neutral cleaner will remove general dirt. Avoid

alkaline soap. Good quality mats inside and outside of entrances will assist in reducing the effects of dirt and damp.

SAFETY

When sanding and sealing floors protective clothing should be worn including a face mask for dust filtration. All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure. Applicators, cloths etc impregnated with the product should be put in a bucket of water and placed outside the building to avoid the possibility of spontaneous combustion. The contents should be disposed of according to local regulations.

ORDERING

Available through distributors worldwide. All products are sold subject to the Company's Standard Conditions of Sale. The Company and its representatives are often asked to comment on the potential uses of Timberex products which differ from those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by Timberex International.



Timberex International

RUST-OLEUM MATHYS

Kolenbergstraat 23

B-3545 Zelem - Belgium

Tel: +32 (0)13 460 0200 - Fax: +32 (0) 13 460 0219

www.timberex.com

